

HEAD OFFICE:


8 PROP STREET, SELBY EXT. 11, JOHANNESBURG, 2001
 PO BOX 6014, JOHANNESBURG, 2000
 TEL: +27 (11)493 7956/9 - 493 7960/1/5 | FAX: +27 (11) 493 0260
 EMAIL: ROPECONS@ROPECON.CO.ZA - WWW.ROPECON.CO.ZA

DURBAN:

14C BOUGAINVILLEA RD
 QUEENSBOROUGH
 TEL: +27 (31) 463 1687
 FAX: +27 (31) 463 1018

CAPE TOWN:

4B BUTSKOP RD
 BLACKHEATH
 TEL: +27 (21) 905 9465
 FAX: +27 (21) 905 1980



For: Mining, Staying etc
Characteristics :Low Stretch, Excellent abrasion resistance, less bending fatigue resistance

DIAMETER		Steel Wire Rope Cross Section mm ²	Steel Wire Rope weight Kg / m	MBL 1770mpa KN
Steel Wire Rope mm	Wire Dia. mm			
6	0.64	14	0.12	22
7	0.74	18	0.16	29
8	0.86	25	0.22	39
9	0.96	31	0.27	49
10	1.06	38	0.33	60
11	1.18	47	0.41	74
12	1.28	55	0.49	87
13	1.38	64	0.56	102
14	1.48	74	0.65	117
15	1.59	85	0.75	135
16	1.71	98	0.86	156
17	1.80	109	0.96	173
18	1.92	124	1.09	197
19	2.01	136	1.20	216
20	2.12	151	1.33	240
21	2.22	166	1.46	263
22	2.33	182	1.61	290